



Custom COP EVOH PCTFE

Thermoformable, FDA-compliant, Pharmaceutical-Grade lamination. Tekni-Plex offers a wide range of film structures to meet both performance and cost requirements

TEKNIFLEX®	Construction		WVTR 38°C, 90% RH (g/m ² /d)	WVTR 38°C, 90% RH (g/100in ² /d)	OTR 23°C, 50% RH (cm ³ /m ² /d)
1703151	20 µm COP . 10 µm EVOH (27 mol%) . 15 µm PCTFE	0.8 mil COP . 0.4 mil EVOH (27 mol%) . 0.6 mil PCTFE	0,38	0,025	0,42

For additional information, please [contact us](#).

Tekni-Films USA: info.teknifilmsNA@tekni-plex.com

Tekni-Plex Europe: info.teknifilmsEUR@tekni-plex.com • +32 53 650 711

Tekni-Plex Gallazzi: info.teknifilmsEUR@tekni-plex.com • +39 0331 815 211

Tekni-Films South America: info.teknifilmsSA@tekni-plex.com • +54 11 4605 4042

www.tekni-plex.com

DISCLAIMER: The information set forth in this datasheet is subject to change without notice and must be confirmed at time of purchase. No licenses, patent, or other intellectual property rights of Tekni-Plex or others are conveyed hereby. TEKNI-PLEX MAKES NO WARRANTY, EXPRESS OR IMPLIED, WITH RESPECT TO THIS INFORMATION AND DISCLAIMS ALL LIABILITY FROM RELIANCE ON IT. Tekni-Plex's only warranties for this product are those written warranties as may be agreed to by Tekni-Plex and its customers in a signed document. TEKNI-PLEX SPECIFICALLY DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, WITH RESPECT TO THE PRODUCT, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSE. Nothing herein shall constitute or imply any promise to enter into any business relationship with Tekni-Plex.