



Custom PE COC EVOH PE

Custom COC, EVOH and PE coextrusion film. Tekni-Plex offers a wide range of film structures to meet both performance and cost requirements.

	Construction	WVTR 38°C, 90% RH (g/m²/d)	WVTR 38°C, 90% RH (g/100in²/d)	OTR 23°C, 50% RH (cm³/m²/d)	OTR 23°C, 50% RH (cm³/in²/d)
2101211	120 µm PE . 10 µm EVOH . 50 µm COC . 75 µm PE	4.7 mil PE . 0.4 mil EVOH . 2.0 mil COC . 3.0 mil PE	0,6	0,04	0,42
2101212	110 µm PE . 10 µm EVOH . 75 µm COC . 110 µm PE	4.3 mil PE . 0.4 mil EVOH . 3.0 mil COC . 4.3 mil PE	0,5	0,03	0,42

DISCLAIMER: The information set forth in this datasheet is subject to change without notice and must be confirmed at time of purchase. No licenses, patent, or other intellectual property rights of Tekni-Plex or others are conveyed hereby. TEKNI-PLEX MAKES NO WARRANTY, EXPRESS OR IMPLIED, WITH RESPECT TO THIS INFORMATION AND DISCLAIMS ALL LIABILITY FROM RELIANCE ON IT. Tekni-Plex's only warranties for this product are those written warranties as may be agreed to by Tekni-Plex and its customers in a signed document. TEKNI-PLEX SPECIFICALLY DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, WITH RESPECT TO THE PRODUCT, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSE. Nothing herein shall constitute or imply any promise to enter into any business relationship.

