

Tekniflex® PX WH

TEKNIFLEX®	Construction		WVTR 38°C, 90% RH (g/m²/d)	WVTR 38°C, 90% RH (g/100in²/d)	OTR 23°C, 50% RH (cm³/m²/d)	OTR 23°C, 50% RH (cm³/100in²/d)
PX7 WH	178 µm PX WH	7.0 mil PX WH	9	0,58	21	1,4
PX8 WH	203 µm PX WH	8.0 mil PX WH	7,8	0,5	19	1,2
PX10 WH	254 µm PX WH	10 mil PX WH	6,2	0,4	15	0,99

TEKNIFLEX®	Construction		WVTR 38°C, 90% RH (g/m²/d)	WVTR 38°C, 90% RH (g/100in²/d)	OTR 23°C, 50% RH (cm³/m²/d)	OTR 23°C, 50% RH (cm³/100in²/d)
PX12 WH	305 µm PX WH	12 mil PX WH	5,2	0,33	13	0,83
PX15 WH	381 µm PX WH	15 mil PX WH	4,2	0,27	9,5	0,61
PX16 WH	406 µm PX WH	16 mil PX WH	3,9	0,25	9,4	0,61
PX18 WH	457 µm PX WH	18 mil PX WH	3,5	0,23	8,3	0,54
PX20 WH	508 µm PX WH	20 mil PX WH	3,1	0,19	7,5	0,49
PX22 WH	559 µm PX WH	22 mil PX WH	2,9	0,19	6,5	0,42
PX25 WH	635 µm PX WH	25 mil PX WH	2,5	0,16	6	0,39
PX30 WH	762 µm PX WH	30 mil PX WH	2,1	0,13	5	0,32
PX35 WH	889 µm PX WH	35 mil PX WH	1,8	0,11	4,3	0,28
PX40 WH	1.016 µm PX WH	40 mil PX WH	1,6	0,1	3,6	0,23
PX45 WH	1.143 µm PX WH	45 mil PX WH	1,4	0,09	3,3	0,22
PX50 WH	1.270 µm PX WH	50 mil PX WH	1,2	0,08	3	0,19
PX55 WH	1.397 µm PX WH	55 mil PX WH	1,1	0,07	2,7	0,18

Available in clear, white, blue tint. EasyStack provides superior denesting properties. Silicone coated PX also available.

For additional information, please [contact us](#).

Tekni-Films USA: info.teknifilmsNA@tekni-plex.com

Tekni-Plex Europe: info.teknifilmsEUR@tekni-plex.com • +32 53 650 711

Tekni-Plex Gallazzi: info.teknifilmsEUR@tekni-plex.com • +39 0331 815 211

Tekni-Films South America: info.teknifilmsSA@tekni-plex.com • +54 11 4605 4042

www.tekni-plex.com

DISCLAIMER: The information set forth in this datasheet is subject to change without notice and must be confirmed at time of purchase. No licenses, patent, or other intellectual property rights of Tekni-Plex or others are conveyed hereby. TEKNI-PLEX MAKES NO WARRANTY, EXPRESS OR IMPLIED, WITH RESPECT TO THIS INFORMATION AND DISCLAIMS ALL LIABILITY FROM RELIANCE ON IT. Tekni-Plex's only warranties for this product are those written warranties as may be agreed to by Tekni-Plex and its customers in a signed document. TEKNI-PLEX SPECIFICALLY DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, WITH RESPECT TO THE PRODUCT, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSE. Nothing herein shall constitute or imply any promise to enter into any business.

TEKNI PLEX®