

[illegible]

TEKNIFLEX®	Construction		WVTR 38°C, 90% RH (g/m²/d)	WVTR 38°C, 90% RH (g/100in²/d)	OTR 23°C, 5% RH (cm³/m²/d)
VPOA760 WH	191 µm PVC WH / 70 µm PE.EVOH.PE / 15 µm PCTFE	7.5 mil PVC WH / 2.8 mil PE.EVOH.PE / 0.6 mil PCTFE	0,37	0,024	0,42
VPOA780 WH	191 µm PVC WH / 70 µm PE.EVOH.PE / 20 µm PCTFE	7.5 mil PVC WH / 2.8 mil PE.EVOH.PE / 0.8 mil PCTFE	0,28	0,018	0,42
VPOA790 WH	191 µm PVC WH / 70 µm PE.EVOH.PE / 23 µm PCTFE	7.5 mil PVC WH / 2.8 mil PE.EVOH.PE / 0.9 PCTFE	0,23	0,015	0,42
VPOA1060 WH	254 µm PVC WH / 70 µm PE.EVOH.PE / 15 µm PCTFE	10.0 mil PVC WH / 2.8 mil PE.EVOH.PE / 0.6 mil PCTFE	0,37	0,024	0,42
VPOA1080 WH	254 µm PVC WH / 70 µm PE.EVOH.PE / 20 µm PCTFE	10.0 mil PVC WH / 2.8 mil PE.EVOH.PE / 0.8 mil PCTFE	0,28	0,018	0,42
VPOA1090 WH	254 µm PVC WH / 70 µm PE.EVOH.PE / 23 µm PCTFE	10.0 mil PVC WH / 2.8 mil PE.EVOH.PE / 0.9 PCTFE	0,23	0,015	0,42
VPOA1260 WH	305 µm PVC WH / 70 µm PE.EVOH.PE / 15 µm PCTFE	12.0 mil PVC WH / 2.8 mil PE.EVOH.PE / 0.6 mil PCTFE	0,37	0,024	0,42
VPOA1280 WH	305 µm PVC WH / 70 µm PE.EVOH.PE / 20 µm PCTFE	12.0 mil PVC WH / 2.8 mil PE.EVOH.PE / 0.8 mil PCTFE	0,28	0,018	0,42
VPOA1290 WH	305 µm PVC WH / 70 µm PE.EVOH.PE / 23 µm PCTFE	12.0 mil PVC WH / 2.8 mil PE.EVOH.PE / 0.9 PCTFE	0,23	0,015	0,42
VPOA1560 WH	381 µm PVC WH / 70 µm PE.EVOH.PE / 15 µm PCTFE	15.0 mil PVC WH / 2.8 mil PE.EVOH.PE / 0.6 mil PCTFE	0,37	0,024	0,42
VPOA1580 WH	381 µm PVC WH / 70 µm PE.EVOH.PE / 20 µm PCTFE	15.0 mil PVC WH / 2.8 mil PE.EVOH.PE / 0.8 mil PCTFE	0,28	0,018	0,42
VPOA1590 WH	381 µm PVC WH / 70 µm PE.EVOH.PE / 23 µm PCTFE	15.0 mil PVC WH / 2.8 mil PE.EVOH.PE / 0.9 PCTFE	0,23	0,015	0,42
VPOA7170 WH	191 µm PVC WH / 70 µm PE.EVOH.PE / 43 µm PCTFE	7.5 mil PVC WH / 2.8 mil PE.EVOH.PE / 1.7 mil PCTFE	0,15	0,01	0,42
VPOA7200 WH	191 µm PVC WH / 70 µm PE.EVOH.PE / 51 µm PCTFE	7.5 mil PVC WH / 2.8 mil PE.EVOH.PE / 2.0 mil PCTFE	0,11	0,007	0,42
VPOA7300 WH	191 µm PVC WH / 70 µm PE.EVOH.PE / 76 µm PCTFE	7.5 mil PVC WH / 2.8 mil PE.EVOH.PE / 3.0 mil PCTFE	0,07	0,005	0,42
VPOA7400 WH	191 µm PVC WH / 70 µm PE.EVOH.PE / 102 µm PCTFE	7.5 mil PVC WH / 2.8 mil PE.EVOH.PE / 4.0 mil PCTFE	0,056	0,004	0,42
VPOA7540 WH	191 µm PVC WH / 70 µm PE.EVOH.PE / 137 µm PCTFE	7.5 mil PVC WH / 2.8 mil PE.EVOH.PE / 5.4 mil PCTFE	0,04	0,003	0,42
VPOA7600 WH	191 µm PVC WH / 70 µm PE.EVOH.PE / 152 µm PCTFE	7.5 mil PVC WH / 2.8 mil PE.EVOH.PE / 6.0 mil PCTFE	0,036	0,002	0,42
VPOA10170 WH	254 µm PVC WH / 70 µm PE.EVOH.PE / 43 µm PCTFE	10.0 mil PVC WH / 2.8 mil PE.EVOH.PE / 1.7 mil PCTFE	0,15	0,01	0,42
VPOA10200 WH	254 µm PVC WH / 70 µm PE.EVOH.PE / 51 µm PCTFE	10.0 mil PVC WH / 2.8 mil PE.EVOH.PE / 2.0 mil PCTFE	0,11	0,007	0,42

TEKNIFLEX®	Construction		WVTR 38°C, 90% RH (g/m²/d)	WVTR 38°C, 90% RH (g/100in²/d)	OT 23°C, RH (cm³/m²/d)
VPOA10300 WH	254 µm PVC WH / 70 µm PE.EVOH.PE / 76 µm PCTFE	10.0 mil PVC WH / 2.8 mil PE.EVOH.PE / 3.0 mil PCTFE	0,07	0,005	0,4
VPOA10400 WH	254 µm PVC WH / 70 µm PE.EVOH.PE / 102 µm PCTFE	10.0 mil PVC WH / 2.8 mil PE.EVOH.PE / 4.0 mil PCTFE	0,056	0,004	0,4
VPOA10540 WH	254 µm PVC WH / 70 µm PE.EVOH.PE / 137 µm PCTFE	10.0 mil PVC WH / 2.8 mil PE.EVOH.PE / 5.4 mil PCTFE	0,04	0,003	0,4
VPOA10600 WH	254 µm PVC WH / 70 µm PE.EVOH.PE / 152 µm PCTFE	10.0 mil PVC WH / 2.8 mil PE.EVOH.PE / 6.0 mil PCTFE	0,036	0,002	0,4
VPOA12170 WH	305 µm PVC WH / 70 µm PE.EVOH.PE / 43 µm PCTFE	12.0 mil PVC WH / 2.8 mil PE.EVOH.PE / 1.7 mil PCTFE	0,15	0,01	0,4
VPOA12200 WH	305 µm PVC WH / 70 µm PE.EVOH.PE / 51 µm PCTFE	12.0 mil PVC WH / 2.8 mil PE.EVOH.PE / 2.0 mil PCTFE	0,11	0,007	0,4
VPOA12300 WH	305 µm PVC WH / 70 µm PE.EVOH.PE / 76 µm PCTFE	12.0 mil PVC WH / 2.8 mil PE.EVOH.PE / 3.0 mil PCTFE	0,07	0,005	0,4
VPOA12400 WH	305 µm PVC WH / 70 µm PE.EVOH.PE / 102 µm PCTFE	12.0 mil PVC WH / 2.8 mil PE.EVOH.PE / 4.0 mil PCTFE	0,056	0,004	0,4
VPOA12540 WH	305 µm PVC WH / 70 µm PE.EVOH.PE / 137 µm PCTFE	12.0 mil PVC WH / 2.8 mil PE.EVOH.PE / 5.4 mil PCTFE	0,04	0,003	0,4
VPOA12600 WH	305 µm PVC WH / 70 µm PE.EVOH.PE / 152 µm PCTFE	12.0 mil PVC WH / 2.8 mil PE.EVOH.PE / 6.0 mil PCTFE	0,036	0,002	0,4
VPOA15170 WH	381 µm PVC WH / 70 µm PE.EVOH.PE / 43 µm PCTFE	15.0 mil PVC WH / 2.8 mil PE.EVOH.PE / 1.7 mil PCTFE	0,15	0,01	0,4
VPOA15200 WH	381 µm PVC WH / 70 µm PE.EVOH.PE / 51 µm PCTFE	15.0 mil PVC WH / 2.8 mil PE.EVOH.PE / 2.0 mil PCTFE	0,11	0,007	0,4
VPOA15300 WH	381 µm PVC WH / 70 µm PE.EVOH.PE / 76 µm PCTFE	15.0 mil PVC WH / 2.8 mil PE.EVOH.PE / 3.0 mil PCTFE	0,07	0,005	0,4
VPOA15400 WH	381 µm PVC WH / 70 µm PE.EVOH.PE / 102 µm PCTFE	15.0 mil PVC WH / 2.8 mil PE.EVOH.PE / 4.0 mil PCTFE	0,056	0,004	0,4
VPOA15540 WH	381 µm PVC WH / 70 µm PE.EVOH.PE / 137 µm PCTFE	15.0 mil PVC WH / 2.8 mil PE.EVOH.PE / 5.4 mil PCTFE	0,04	0,003	0,4
VPOA15600 WH	381 µm PVC WH / 70 µm PE.EVOH.PE / 152 µm PCTFE	15.0 mil PVC WH / 2.8 mil PE.EVOH.PE / 6.0 mil PCTFE	0,036	0,002	0,4

For more detailed information for PVC, please [contact us](#).

Tekni-Films USA: info.teknifilmsNA@tekni-plex.com

Tekni-Plex Europe: info.teknifilmsEUR@tekni-plex.com • +32 53 650 711

Tekni-Plex Gallazzi: info.teknifilmsEUR@tekni-plex.com • +39 0331 815 211

Tekni-Films South America: info.teknifilmsSA@tekni-plex.com • +54 11 4605 4042

www.tekni-plex.com

DISCLAIMER: The information set forth in this datasheet is subject to change without notice and must be confirmed at time of purchase. No licenses, patent, or other intellectual property rights of Tekni-Plex or others are conveyed hereby. TEKNI-PLEX MAKES NO WARRANTY, EXPRESS OR IMPLIED, WITH RESPECT TO THIS INFORMATION AND DISCLAIMS ALL LIABILITY FROM RELIANCE ON IT. Tekni-Plex's only warranties for this product are those written warranties as may be agreed to by Tekni-Plex and its customers in a signed document. TEKNI-PLEX SPECIFICALLY DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, WITH RESPECT TO THE PRODUCT, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSE. Nothing herein shall constitute or imply any promise to enter into any business

TEKNI PLEX®