

[illegible]

TEKNIFLEX®	Construction		WVTR 38°C, 90% RH (g/m²/d)	WVTR 38°C, 90% RH (g/100in²/d)	OTR 23°C, 50% RH (cm³/m²/d)	23°C (cm³/m²/d)
VPOA760	191 µm PVC / 70 µm PE.EVOH.PE / 15 µm PCTFE	7.5 mil PVC / 2.8 mil PE.EVOH.PE / 0.6 mil PCTFE	0,37	0,024	0,42	

TEKNIFLEX®	Construction		WVTR 38°C, 90% RH (g/m²/d)	WVTR 38°C, 90% RH (g/100in²/d)	OTR 23°C, 50% RH (cm³/m²/d)
VPOA780	191 µm PVC / 70 µm PE.EVOH.PE / 20 µm PCTFE	7.5 mil PVC / 2.8 mil PE.EVOH.PE / 0.8 mil PCTFE	0,28	0,018	0,42
VPOA790	191 µm PVC / 70 µm PE.EVOH.PE / 23 µm PCTFE	7.5 mil PVC / 2.8 mil PE.EVOH.PE / 0.9 PCTFE	0,23	0,015	0,42
VPOA1060	254 µm PVC / 70 µm PE.EVOH.PE / 15 µm PCTFE	10.0 mil PVC / 2.8 mil PE.EVOH.PE / 0.6 mil PCTFE	0,37	0,024	0,42
VPOA1080	254 µm PVC / 70 µm PE.EVOH.PE / 20 µm PCTFE	10.0 mil PVC / 2.8 mil PE.EVOH.PE / 0.8 mil PCTFE	0,28	0,018	0,42
VPOA1090	254 µm PVC / 70 µm PE.EVOH.PE / 23 µm PCTFE	10.0 mil PVC / 2.8 mil PE.EVOH.PE / 0.9 PCTFE	0,23	0,015	0,42
VPOA1260	305 µm PVC / 70 µm PE.EVOH.PE / 15 µm PCTFE	12.0 mil PVC / 2.8 mil PE.EVOH.PE / 0.6 mil PCTFE	0,37	0,024	0,42
VPOA1280	305 µm PVC / 70 µm PE.EVOH.PE / 20 µm PCTFE	12.0 mil PVC / 2.8 mil PE.EVOH.PE / 0.8 mil PCTFE	0,28	0,018	0,42
VPOA1290	305 µm PVC / 70 µm PE.EVOH.PE / 23 µm PCTFE	12.0 mil PVC / 2.8 mil PE.EVOH.PE / 0.9 PCTFE	0,23	0,015	0,42
VPOA1560	381 µm PVC / 70 µm PE.EVOH.PE / 15 µm PCTFE	15.0 mil PVC / 2.8 mil PE.EVOH.PE / 0.6 mil PCTFE	0,37	0,024	0,42
VPOA1580	381 µm PVC / 70 µm PE.EVOH.PE / 20 µm PCTFE	15.0 mil PVC / 2.8 mil PE.EVOH.PE / 0.8 mil PCTFE	0,28	0,018	0,42
VPOA1590	381 µm PVC / 70 µm PE.EVOH.PE / 23 µm PCTFE	15.0 mil PVC / 2.8 mil PE.EVOH.PE / 0.9 PCTFE	0,23	0,015	0,42
VPOA7170	191 µm PVC / 70 µm PE.EVOH.PE / 43 µm PCTFE	7.5 mil PVC / 2.8 mil PE.EVOH.PE / 1.7 mil PCTFE	0,15	0,01	0,42
VPOA7200	191 µm PVC / 70 µm PE.EVOH.PE / 51 µm PCTFE	7.5 mil PVC / 2.8 mil PE.EVOH.PE / 2.0 mil PCTFE	0,11	0,007	0,42
VPOA7300	191 µm PVC / 70 µm PE.EVOH.PE / 76 µm PCTFE	7.5 mil PVC / 2.8 mil PE.EVOH.PE / 3.0 mil PCTFE	0,07	0,005	0,42
VPOA7400	191 µm PVC / 70 µm PE.EVOH.PE / 102 µm PCTFE	7.5 mil PVC / 2.8 mil PE.EVOH.PE / 4.0 mil PCTFE	0,056	0,004	0,42
VPOA7540	191 µm PVC / 70 µm PE.EVOH.PE / 137 µm PCTFE	7.5 mil PVC / 2.8 mil PE.EVOH.PE / 5.4 mil PCTFE	0,04	0,003	0,42
VPOA7600	191 µm PVC / 70 µm PE.EVOH.PE / 152 µm PCTFE	7.5 mil PVC / 2.8 mil PE.EVOH.PE / 6.0 mil PCTFE	0,036	0,002	0,42
VPOA10170	254 µm PVC / 70 µm PE.EVOH.PE / 43 µm PCTFE	10.0 mil PVC / 2.8 mil PE.EVOH.PE / 1.7 mil PCTFE	0,15	0,01	0,42
VPOA10200	254 µm PVC / 70 µm PE.EVOH.PE / 51 µm PCTFE	10.0 mil PVC / 2.8 mil PE.EVOH.PE / 2.0 mil PCTFE	0,11	0,007	0,42
VPOA10300	254 µm PVC / 70 µm PE.EVOH.PE / 76 µm PCTFE	10.0 mil PVC / 2.8 mil PE.EVOH.PE / 3.0 mil PCTFE	0,07	0,005	0,42

TEKNIFLEX®	Construction		WVTR 38°C, 90% RH (g/m²/d)	WVTR 38°C, 90% RH (g/100in²/d)	OTR 23°C, 50% RH (cm³/m²/d)
VPOA10400	254 µm PVC / 70 µm PE.EVOH.PE / 102 µm PCTFE	10.0 mil PVC / 2.8 mil PE.EVOH.PE / 4.0 mil PCTFE	0,056	0,004	0,42
VPOA10540	254 µm PVC / 70 µm PE.EVOH.PE / 137 µm PCTFE	10.0 mil PVC / 2.8 mil PE.EVOH.PE / 5.4 mil PCTFE	0,04	0,003	0,42
VPOA10600	254 µm PVC / 70 µm PE.EVOH.PE / 152 µm PCTFE	10.0 mil PVC / 2.8 mil PE.EVOH.PE / 6.0 mil PCTFE	0,036	0,002	0,42
VPOA12170	305 µm PVC / 70 µm PE.EVOH.PE / 43 µm PCTFE	12.0 mil PVC / 2.8 mil PE.EVOH.PE / 1.7 mil PCTFE	0,15	0,01	0,42
VPOA12200	305 µm PVC / 70 µm PE.EVOH.PE / 51 µm PCTFE	12.0 mil PVC / 2.8 mil PE.EVOH.PE / 2.0 mil PCTFE	0,11	0,007	0,42
VPOA12300	305 µm PVC / 70 µm PE.EVOH.PE / 76 µm PCTFE	12.0 mil PVC / 2.8 mil PE.EVOH.PE / 3.0 mil PCTFE	0,07	0,005	0,42
VPOA12400	305 µm PVC / 70 µm PE.EVOH.PE / 102 µm PCTFE	12.0 mil PVC / 2.8 mil PE.EVOH.PE / 4.0 mil PCTFE	0,056	0,004	0,42
VPOA12540	305 µm PVC / 70 µm PE.EVOH.PE / 137 µm PCTFE	12.0 mil PVC / 2.8 mil PE.EVOH.PE / 5.4 mil PCTFE	0,04	0,003	0,42
VPOA12600	305 µm PVC / 70 µm PE.EVOH.PE / 152 µm PCTFE	12.0 mil PVC / 2.8 mil PE.EVOH.PE / 6.0 mil PCTFE	0,036	0,002	0,42
VPOA15170	381 µm PVC / 70 µm PE.EVOH.PE / 43 µm PCTFE	15.0 mil PVC / 2.8 mil PE.EVOH.PE / 1.7 mil PCTFE	0,15	0,01	0,42
VPOA15200	381 µm PVC / 70 µm PE.EVOH.PE / 51 µm PCTFE	15.0 mil PVC / 2.8 mil PE.EVOH.PE / 2.0 mil PCTFE	0,11	0,007	0,42
VPOA15300	381 µm PVC / 70 µm PE.EVOH.PE / 76 µm PCTFE	15.0 mil PVC / 2.8 mil PE.EVOH.PE / 3.0 mil PCTFE	0,07	0,005	0,42
VPOA15400	381 µm PVC / 70 µm PE.EVOH.PE / 102 µm PCTFE	15.0 mil PVC / 2.8 mil PE.EVOH.PE / 4.0 mil PCTFE	0,056	0,004	0,42
VPOA15540	381 µm PVC / 70 µm PE.EVOH.PE / 137 µm PCTFE	15.0 mil PVC / 2.8 mil PE.EVOH.PE / 5.4 mil PCTFE	0,04	0,003	0,42
VPOA15600	381 µm PVC / 70 µm PE.EVOH.PE / 152 µm PCTFE	15.0 mil PVC / 2.8 mil PE.EVOH.PE / 6.0 mil PCTFE	0,036	0,002	0,42

Available in clear, white. PX may be substituted for PVC.

For additional information, please [contact us](#).

Tekni-Films USA: info.teknifilmsNA@tekni-plex.com

Tekni-Plex Europe: info.teknifilmsEUR@tekni-plex.com • +32 53 650 711

Tekni-Plex Gallazzi: info.teknifilmsEUR@tekni-plex.com • +39 0331 815 211

Tekni-Films South America: info.teknifilmsSA@tekni-plex.com • +54 11 4605 4042

www.tekni-plex.com

DISCLAIMER: The information set forth in this datasheet is subject to change without notice and must be confirmed at time of purchase. No licenses, patent, or other intellectual property rights of Tekni-Plex or others are conveyed hereby. TEKNI-PLEX MAKES NO WARRANTY, EXPRESS OR IMPLIED, WITH RESPECT TO THIS INFORMATION AND DISCLAIMS ALL LIABILITY FROM RELIANCE ON IT. Tekni-Plex's only warranties for this product are those written warranties as may be agreed to by Tekni-Plex and its customers in a signed document. TEKNI-PLEX SPECIFICALLY DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, WITH RESPECT TO THE PRODUCT, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSE. Nothing herein shall constitute or imply any promise to enter into any business

TEKNI PLEX®