

TEKNIMD®	Construction		WVTR 38°C, 90% RH (g/m²/d)	WVTR 38°C, 90% RH (g/100in²/d)	OTR 23°C, 50% RH (cm³/m²/d)	OTR 23°C, 50% RH (cm³/100in²/d)
PXA3060	762 µm PX / 15 µm PCTFE	30 mil PX / 0.6 mil PCTFE	0,36	0,023	4,6	0,3
PXA3080	762 µm PX / 20 µm PCTFE	30 mil PX / 0.8 mil PCTFE	0,27	0,017	4,5	0,29
PXA3090	762 µm PX / 23 µm PCTFE	30 mil PX / 0.9 mil PCTFE	0,24	0,015	4,5	0,29
PXA4060	1.016 µm PX / 15 µm PCTFE	40 mil PX / 0.6 mil PCTFE	0,36	0,023	3,5	0,23
PXA4080	1.016 µm PX / 20 µm PCTFE	40 mil PX / 0.8 mil PCTFE	0,27	0,017	3,4	0,22
PXA4090	1.016 µm PX / 23 µm PCTFE	40 mil PX / 0.9 mil PCTFE	0,24	0,015	3,4	0,22
PXA5060	1.270 µm PX / 15 µm PCTFE	50 mil PX / 0.6 mil PCTFE	0,36	0,023	2,8	0,18
PXA5080	1.270 µm PX / 20 µm PCTFE	50 mil PX / 0.8 mil PCTFE	0,27	0,017	2,8	0,18
PXA5090	1.270 µm PX / 23 µm PCTFE	50 mil PX / 0.9 mil PCTFE	0,24	0,015	2,7	0,17
PXA30170	762 µm PX / 43 µm PCTFE	30 mil PX / 1.7 mil PCTFE	0,15	0,01	4,3	0,28

TEKNIMD®	Construction		WVTR 38°C, 90% RH (g/m²/d)	WVTR 38°C, 90% RH (g/100in²/d)	OTR 23°C, 50% RH (cm³/m²/d)	OTR 23°C, 50% RH (cm³/100in²/d)
PXA30200	762 µm PX / 51 µm PCTFE	30 mil PX / 2.0 mil PCTFE	0,11	0,007	4,2	0,27
PXA30300	762 µm PX / 76 µm PCTFE	30 mil PX / 3.0 mil PCTFE	0,074	0,005	4	0,26
PXA30400	762 µm PX / 102 µm PCTFE	30 mil PX / 4.0 mil PCTFE	0,054	0,003	3,8	0,25
PXA30540	762 µm PX / 137 µm PCTFE	30 mil PX / 5.4 mil PCTFE	0,04	0,003	3,5	0,23
PXA30600	762 µm PX / 152 µm PCTFE	30 mil PX / 6.0 mil PCTFE	0,037	0,002	3,5	0,23
PXA40170	1.016 µm PX / 43 µm PCTFE	40 mil PX / 1.7 mil PCTFE	0,15	0,01	3,3	0,21
PXA40200	1.016 µm PX / 51 µm PCTFE	40 mil PX / 2.0 mil PCTFE	0,11	0,007	3,2	0,21
PXA40300	1.016 µm PX / 76 µm PCTFE	40 mil PX / 3.0 mil PCTFE	0,074	0,005	3,1	0,2
PXA40400	1.016 µm PX / 102 µm PCTFE	40 mil PX / 4.0 mil PCTFE	0,054	0,003	3	0,19
PXA40540	1.016 µm PX / 137 µm PCTFE	40 mil PX / 5.4 mil PCTFE	0,04	0,003	2,8	0,18
PXA40600	1.016 µm PX / 152 µm PCTFE	40 mil PX / 6.0 mil PCTFE	0,037	0,002	2,8	0,18
PXA50170	1.270 µm PX / 43 µm PCTFE	50 mil PX / 1.7 mil PCTFE	0,15	0,01	2,7	0,17
PXA50200	1.270 µm PX / 51 µm PCTFE	50 mil PX / 2.0 mil PCTFE	0,11	0,007	2,6	0,17
PXA50300	1.270 µm PX / 76 µm PCTFE	50 mil PX / 3.0 mil PCTFE	0,074	0,005	2,6	0,17
PXA50400	1.270 µm PX / 102 µm PCTFE	50 mil PX / 4.0 mil PCTFE	0,054	0,003	2,5	0,16
PXA50550	1.270 µm PX / 137 µm PCTFE	50 mil PX / 5.4 mil PCTFE	0,04	0,003	2,4	0,15
PXA50600	1.270 µm PX / 152 µm PCTFE	50 mil PX / 6.0 mil PCTFE	0,037	0,002	2,3	0,15

Available in clear, white, blue tint. Alternative PX thicknesses are available upon request.

For additional information, please [contact us](#).

Tekni-Films USA: info.teknifilmsNA@tekni-plex.com

Tekni-Plex Europe: info.teknifilmsEUR@tekni-plex.com • +32 53 650 711

Tekni-Plex Gallazzi: info.teknifilmsEUR@tekni-plex.com • +39 0331 815 211

Tekni-Films South America: info.teknifilmsSA@tekni-plex.com • +54 11 4605 4042

www.tekni-plex.com

DISCLAIMER: The information set forth in this datasheet is subject to change without notice and must be confirmed at time of purchase. No licenses, patent, or other intellectual property rights of Tekni-Plex or others are conveyed hereby. TEKNI-PLEX MAKES NO WARRANTY, EXPRESS OR IMPLIED, WITH RESPECT TO THIS INFORMATION AND DISCLAIMS ALL LIABILITY FROM RELIANCE ON IT. Tekni-Plex's only warranties for this product are those written warranties as may be agreed to by Tekni-Plex and its customers in a signed document. TEKNI-PLEX SPECIFICALLY DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, WITH RESPECT TO THE PRODUCT, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSE. Nothing herein shall constitute or imply any promise to enter into any business

TEKNI PLEX